

## Energy Reduction Initiatives to Improve Low Amperage Cell Performance

Amit Gupta<sup>1</sup>, Amit Jha<sup>2</sup>, Mahesh Sahoo<sup>3</sup>, Ravi Pandey<sup>4</sup>, Maneesh VT<sup>5</sup> and J. P. Nayak<sup>6</sup>

1. Senior Scientist

2. Senior Scientist

Aditya Birla Science and Technology Co. Pvt. Ltd, MIDC, Taloja, Panvel, Maharashtra, India

3. Head - Technical

4. Head - Potroom

5. Head - Production

6. Head - Smelter

Hindalco Industries Ltd, HiraKud, Sambalpur, Odisha, India

Corresponding author: [amit.gupta@adityabirla.com](mailto:amit.gupta@adityabirla.com)

### Abstract

DOWNLOAD  
FULL PAPER



Incessantly increasing energy prices and low London Metal Exchange (LME) aluminium prices have forced aluminium smelters to reduce energy consumption. HINDALCO HiraKud has four end-to-end prebake potlines with 680 cells altogether, operating at 85 kA, which were converted from Soederberg potlines with GAMI cell technology in 2006 – 2009. Due to end-to-end busbar configuration, magnetohydrodynamic (MHD) stability hinders anode-to-cathode distance (ACD) reduction. MHD stability is adversely affected by the horizontal currents and uncompensated vertical magnetic field in the molten metal. The cells are designed to be heat conservative; therefore, thermal balance of the cells is critical for voltage reduction. As part of the voltage reduction initiatives, copper-insert collector bars (CuCB) have been installed in a few cells. The impact of CuCB in 85 kA cells and required modifications of cell design were calculated with mathematical models. The CuCB reduce the horizontal currents in the molten metal significantly and thereby improve the MHD stability of the cells. The cell lining was modified to compensate reduced heat generation due to voltage reduction. The trial cells have shown significant increase in pot stability. They have been operating since one year at 280 kWh/t Al lower energy consumption and better current efficiency than regular pots.

**Keywords:** Aluminium reduction cell, copper-insert collector bar, pot stability, thermal balance, low amperage cell.

### 1. Introduction

Aluminium smelting is an energy intensive process where energy cost contribution is around 40 % of the total cost of production. Unceasingly increasing energy price has affected the smelter operating margins considerably, which lead the smelters to take measures on voltage reduction. HiraKud aluminium smelter has four end-to-end prebake potline operating at 85 kA, which were converted from Soederberg potlines with GAMI cell technology during 2006 – 2009. Due to end-to-end busbar configuration of HiraKud potlines, magnetohydrodynamic (MHD) stability hinders reduction in anode-to-cathode distance (ACD). This contributes to around 35 % of the total voltage requirement, also the maximum heat generation takes place in the ACD. Therefore, it is desirable to maintain ACD as low as possible to operate the cell at lower energy, while satisfying the heat balance requirement. MHD stability of cell is adversely affected by the uncompensated vertical magnetic field and the horizontal currents in the molten metal.

To eradicate the uncompensated magnetic field, busbar configuration can be optimized, however it is capital intensive [1]. Besides improving the magnetic field distribution, reduction in the horizontal current using copper insert collector bar (CuCB) is another way to improve the MHD stability of cells and thereby reduce ACD [2, 3]. Since copper has higher electrical conductivity than steel, it alters the electrical resistance path in cathode assembly, resulting in reduction in the horizontal currents in molten metal along with uniform current distribution in the cathode block. Apart from this, it also reduces the cathode voltage drop (CVD), which is attributed to uniform current distribution in the cathode and lower electrical resistivity of copper. Any voltage reduction in CVD or ACD will also lessen the heat generation and thus deteriorating the thermal balance of cell. Since these cells are designed to be heat conservative, it requires careful evaluation for any design modification.

Earlier the authors have reported, the computational analysis on various designs of CuCB and their impact on the current distribution, cathode voltage drop, cathode temperature, ledge profile and structural integrity of the cell [3]. This paper presents the implemented design of CuCB with modified cell lining in Hirkud 85 kA cells and their impact on cell performance. The thermal-electric, electromagnetic and MHD models were utilized to analyze the impact of CuCB. These models were developed using commercial software ANSYS and PHOENICS-ESTER. The steady state condition was simulated for reference cell with normal steel collector bar and for CuCB cell with modified cell lining. The CuCB with modified cell lining have been implemented in few cells. The performance of these cells with respect to voltage breakdown and key operational parameters was monitored over a year.

## **2. Mathematical Modeling**

A 3D quarter cell, thermo-electric model has been used for analyzing the electrical and thermal impact of CuCB. Also 3D full cell electromagnetic and MHD models have been utilized for fluid flow calculation. The models incorporate boundary conditions based on the cell design and operating parameters. More details regarding the governing equations, model development and its validation with the measurements, have been reported earlier [1, 4].

### **2.1. Current Distribution**

As described in previous section, the CuCB alters the electrical resistance path in the cathode and collector bar assembly thereby improving the current distribution in the cell. Figure 1 and Figure 2 show the current distribution in the reference cell and in the CuCB cell respectively. Figure 1 shows that there are significant amount of horizontal currents being generated in the molten metal region. The magnitude of horizontal current in particular cell design depends on cathode material, and collector bar dimensions [5, 6]. From Figure 2 it is evident that use of CuCB reduces the horizontal currents significantly in the metal region.

The erosion of cathode top surface is a function of current density in the cathode block, resulting in non-uniform cathode surface over its life. Apart from reducing the horizontal current in molten metal, CuCB also improves the current density distribution in the cathode block. This would also reduce the non-uniform erosion of cathode surface thereby enhancing the cathode and cell life.

#### 4. Conclusions

As part of the voltage reduction initiatives, the copper insert collector bar (CuCB) was evaluated using mathematical models. Modeling and measurement shows that CuCB provide significant voltage saving potential in low amperage cell, provided the thermal balance is maintained. The cell lining was modified to compensate the reduced heat generation due to voltage reduction. CuCB was installed in few cells of 85 kA potline at Hirkud. Modeling results show significant improvement in current distribution in the metal pad, molten metal velocity and metal-electrolyte interface deformation by using CuCB. Test performed on running cells for pot stability, highlighted the potential of operating the cell with 5 - 6 mm lower ACD than in the reference cells. In spite of higher pot stability attained by CuCB cell, the voltage reduction was limited by thermal balance constraint, as these cells were originally designed to be heat conservative. These cells have been operating for a year at approximately 280 kWh/t Al, lower energy consumption and better current efficiency than reference cells. Cell design is being explored to further reduce the energy at same amperage, by putting more insulation in the cell lining. The optimal design of copper inserts and the cell lining, for a particular cell technology, are the key to achieve low CVD, optimum current distribution and thermal balance.

#### 5. Acknowledgement

The authors would like to thank teams of Hindalco Hirkud and Aditya Birla Science and Technology Co. Pvt. Ltd (ABSTC) for their support in conducting this study.

#### 6. References

1. A. Gupta, S. Namboothiri, M. Chulliparambil, S. Mani, B. Basu, and J. Janardhanan, Electromagnetic and MHD Study to Improve Cell Performance of an End-to-End 86 kA Potline, *Light Metals*, 2012, 853-858.
2. R. Kaenel, J. Antille, L. Bugnion, Impact of Copper Insert Collector Bars, *Light Metals* 2015, 807-812.
3. A. Gupta, A. Jha, M. Sahoo, J. Jinil and J. P. Nayak, Impact of copper insert on low amperage aluminium reduction cell, The International Committee for Study of Bauxite, Alumina & Aluminium, 2015, Dubai, UAE.
4. A. Gupta and S. Namboothiri, Impact of Carbon Seam on Freeze Profile in Aluminium Reduction Cell, *Transactions of the Indian Institute of Metals*, 2017, Volume 70, Issue 6, 1563–1574.
5. W. Li, Y. Zhang, D. Chai, J. Yang, S. Qiu, and Y. Wang, Simulation and Optimization of Cathode Current Distribution to Reduce the Horizontal Current in the Aluminum Liquid, *Light Metals* 2014, TMS, 495-499.
6. A. Gupta, S. Modak, M. Sahoo and J. Janardhanan, Investigation of Cathode & Collector Bar Modification on Thermal Balance of Low Amperage Cell, *Light Metals*, 2015, 747-752.