

Production of Green Direct Reduced Iron (DRI) from Red Mud of Indian Origin: A Novel Concept

Bhagyadhar Bhoi¹, Priyanka Rajput² and Chitta Ranjan Mishra³

1. Chief Scientist

2. Scientist,

CSIR - Institute of Minerals & Materials Technology, Bhubaneswar, Odisha, India

3. Former Deputy General Manager (R&D)

4. National Aluminium Company Limited (NALCO), Bhubaneswar, Odisha, India

Corresponding authors: bbhoi@immt.res.in

Abstract



Red Mud is considered as one of the hazardous waste materials generated during the processing of bauxite for production of alumina using caustic soda employing the Bayer's process. Presently Red Mud is discharged into the nearby Red Mud ponds which are located in the vicinity of alumina refineries. Red Mud of Indian Origin contains around 45-55 % Fe_2O_3 , 10.69 % TiO_2 , 20.42 % Al_2O_3 , 8.72 % SiO_2 and other associated oxides in minor quantities. This composition of Red Mud can be considered as rich source of iron. No significant efforts have been made so far for exploitation of Red Mud for production of iron in commercial scale though some research activities have been reported. R&D activities centered around production of DRI from iron ore have been successfully achieved and reported from this Institute by employing Microwave Hydrogen Plasma Reactor process using hydrogen as reductant at a low temperature of 600-800 °C. In the present study, similar process has been employed for production of DRI from Red Mud using the same reactor. The DRI produced in the process has been characterized through mineralogical and chemical analysis. The by-product "water" produced in the process can be recycled when the process is carried out in a commercial scale.

Keywords: Red mud, microwave hydrogen plasma reactor, green direct reduced iron, water.

1. Introduction

Red Mud of Indian origin contains around 55% plus of Fe_2O_3 and is considered as a hazardous waste material for the alumina industry which is generated in the order of two tons of Red Mud per one tone of alumina produced from bauxite. The worldwide alumina production is around 58 million tonnes in which India counts for 2.7 million tonnes. India produces around 5.4 million tonnes of Red Mud per annum from its various alumina refineries.

Major players in the Indian aluminium sector are INDAL, BALCO, HINDALCO, NALCO, MALCO, and Vedanta Alumina Ltd. Application of Red Mud for production of different value added items like Portland cement [1, 2], bricks & blocks, tiles, paints & pigments, soil amending agents, fibre reinforced polymer composites for building materials as wood substitutes [3] etc., have been tried out by many researchers throughout the world. However these applications have resulted in partial utilization of Red Mud and bulk utilization of Red Mud still remains as a challenge before the global aluminium community. Since iron constitutes as a major ingredient of Red Mud amounting to around 53.6%, the scope of its recovery for production of DRI is considered as a scientific & technological challenge. Efforts have been made for production of pig iron from NALCO Red Mud by application of plasma smelting technology [4]. Since the processes so far developed for production of pig iron employing Plasma Smelting Technology was not devoid of environmental pollution, the efforts were directed for production of Green DRI by using Microwave Hydrogen Plasma Reactor,

considered as a novel and state-of-the-art technology and more so free from environmental hazards. The only by-product that is produced in the process is 'water' which can be recycled for meeting process requirements during scale up of the operation. The process is novel and unique in character and is 100% eco-friendly.

2. Raw Materials

The raw material used for the process was the Red Mud of Indian origin having the following chemical compositions as given in Table 1. The other raw material used for the study was hydrogen gas with 99.9% purity.

Table 1. Typical Composition of Indian Red Mud.

Input Material	Fe₂O₃ (%)	SiO₂ (%)	TiO₂ (%)	Al₂O₃ (%)	Na₂O (%)	MgO (%)	CaO (%)	LOI (%)
Indian Red Mud	53.6	18.9	2.20	4.88	8.29	0.21	0.54	9.30

3. Experimental

The Red Mud of Indian Origin was subjected to crushing and grinding to bring the size up to -100 mesh which was then pelletized to 40X10⁻³m diameter and 3X10⁻³m height using an electrically operated automatic briquetting press by addition of 1-2% of water with respect to the amount of sample taken for the study. This was then dried in the oven at 100°C for 2hrs. The dried pellet was then subjected to Hydrogen Plasma Reduction in Microwave Hydrogen Plasma Reactor. The experimental parameters like Flow of Hydrogen, Reduction Temperature, Reduction Time, Pressure, and the Power input were studied for the reduction of iron content in Red Mud for production of Green DRI. The raw materials and the products were analysed for their chemical compositions and mineralogical characters. The reduction studies were carried out as per the process flow sheet given in Figure 1.

3.1 Microwave Hydrogen Plasma Reduction Process

The reduction of raw Red Mud pellet was carried out in a specially built Microwave Hydrogen Plasma Reactor of 6kW power for production of Green DRI. The plasma is generated by Microwave assisted thermal plasma process. The Schematic Diagram of Microwave Hydrogen Plasma Reactor with in-situ photograph of Reactor Chamber is shown in Figure 2. The system has provision to inject Hydrogen gas from the top into the chamber through a safety valve and the flow of the gas can be controlled by a mass flow controller. The temperature of the Molybdenum sample holder is measured by means of an IR Pyrometer. The microwave power can be varied to generate the plasma over a range of temperature. The high frequency waves interact with the hydrogen gas to produce the hydrogen plasma. The plasma produced in this manner covers a region up to about 6X 10⁻² to 8 X 10⁻² m above the sample. The hydrogen molecules enter the plasma zone and become part of it. The hydrogen molecules under the influence of plasma dissociate in to atomic and ionic forms which reduces the iron oxide present on the surface of Red Mud pellet into metallic iron. These ionic charged particles of hydrogen recombine immediately in to hydrogen molecules when they exit from the plasma zone.

5 Eco-friendly Process

The conventional process of iron making through DRI route has limitations. It requires higher temperature of around 1200°C to convert iron oxide in to metallic iron. In the other hand, the present process needs low temperature of around 300°C only to carry out the reduction and is more energy and cost effective. Furthermore, the process is green in character as it is carbon free and environmental friendly and generates ‘water’ in the process as a by-product which can be recycled when used in the commercial process.

6 Conclusion

From the above experimental evidences and observations, it can be concluded that Red Mud containing around 53.6% Fe₂O₃ and some appreciable quantities of Al₂O₃ and other associated metal oxides in minor quantities, can very well be reduced to Green DRI by application of Microwave Hydrogen Plasma technology.

The process has been successfully established in the laboratory scale and needs to be scaled up to pilot scale of operation before its commercial feasibility is established. CSIR-IMMT, Bhubaneswar, Odisha, India is in possession of laboratory scale technology for production of Green DRI from Red Mud of Indian origin and the know-how is readily available for commercial exploitation.

7 Acknowledgement

The authors are grateful to Prof. (Dr.) B. K.Mishra, Director, CSIR-IMMT, Bhubaneswar for his cooperation and guidance in the R&D work and giving permission for publication of the paper. The authors are also grateful to the Indian aluminium industries for providing Red Mud samples for carrying out the investigation.

8 References

1. K. Jayshankar, P. S. Mukherjee, B. Bhoi, and C. R. Mishra, “Production of Pig iron and Portland Slag Cement from Red Mud by Application of Novel Thermal Plasma Technique”, IBAAS-CHALIECO, 2013, International Aluminium Industry Conference, Nanning, Guangxi, China, IBAAS Binder, November 28-30, 2013, 117-125.
2. C. R. Mishra, D. Yadav, P. S. Sharma, and M. M. Alli, “Production of Ordinary Portland Cement (OPC) from NALCO Red Mud”, Light Metals 2011, Edited by: Stephen J. Lindsay, TMS-2011, 97-102.
3. M. Saxena, and C. R. Mishra, Processing of Red Mud for Development of Wood Substitute,” Global Symposium on Recycling Waste Treatment and Clean Technology (REWAS-2004), Madrid, Spain, Proceedings, Vol. 1, September 26-29, 2004, 371-380.
4. P. S. Mukherjee, B. Bhoi, C.R. Mishra, R.R Dash, B.K. Satapathy, and J. Kalidas, Production of Pig Iron from NALCO Red Mud by Application of Plasma Smelting Technology, Light Metals -2012, Edited by: Carlos E. Suaraz, TMS -2012, 99-103.
5. B. Bhoi, P. Behera, and C. Mishra, Production of Green Steel from Red Mud: A Novel Concept, 6th International Symposium on High- Temperature Metallurgical Processing, (TMS 2015), Walt Disney World, Orlando, Florida, USA, March 15-19, 2015,19-26.
6. K. Kamiya, N. Kitahara, I. Morinaka, K. Sakuraya, M. Ozawa, and M. Tanaka, Trans. ISIJ, 24, (1984), 7-16.
7. H. Hiebler and J.F. Plaul, *Metalurgia*, 43, (2004),155-162.
8. R.G.Gold, W.R.Sandall, P.G.Cheplick and D.R. MacRae, *Ironmak. Steelmak*, Vol. 4, (1977), 10-14.

9. I. Morinaka, K. Kamiya, K. Sakuraya, N. Kitahara, M. Ozawa and M. Tanaka, *Trans. ISIJ*, 20, (1980), 177-186.
10. P. Rajput, B. Bhoi, S. Sahoo, R.K. Paramguru and B.K. Mishra, *Ironmaking and Steelmaking*, 40 (1), (2013), 61-68.