

Extraction of Gallium from Jamaican Bayer Process Operations

Tandose Sambo¹ and Worrell Lyew-You²

1. Chemical Process Engineer

2. Director, Process Monitoring Services

Jamaica Bauxite Institute, Kingston, Jamaica

Corresponding author: tsambo@jbi.org.jm

Abstract

DOWNLOAD
FULL PAPER



Gallium is emerging as a next generation metal that has multiple applications in the semiconductor and solar photovoltaic industry. It is mostly extracted as a byproduct of the production of aluminum and zinc metals. Gallium normally dissolves in the dominant process liquor and is recovered via processes such as solvent extraction and electrolytic processes. As the net-zero initiatives are becoming more pertinent in the global landscape, there is a need for materials that will facilitate green technologies. Gallium is one of those critical minerals that will enable this vision to become a reality. The aim of this paper is to identify the optimum path for the extraction of gallium from Jamaican Bayer process operations. Jamaica has both low and high temperature refinery operations, and there are opportunities to initiate the production of gallium in the future. Gallium in Jamaican bauxite is found to occur in the range of 48–75 $\mu\text{g/g}$, classifying the resource as a medium gallium content bauxite. With an average of 60 $\mu\text{g/g}$ of gallium in bauxite, studies have shown that the critical metal is accumulating in the sodium aluminate process liquor as alumina is produced. This paper outlines the dispersion of gallium through a low temperature Jamaican Bayer process operation and proposes key design elements for optimizing a process that will extract the metal.

Keywords: Gallium, Bayer process, Gallium process balance, Gallium dispersion in the Bayer process.

1. Introduction

A study of the associations of gallium with aluminum and iron minerals has identified that Jamaican bauxites contain gallium concentrations in the range of 48-75 $\mu\text{g/g}$ [1]. The average concentration of gallium in Jamaican bauxites is approximately 60 $\mu\text{g/g}$. According to global standards, this classifies Jamaican bauxites as medium gallium content bauxites. Chemical studies have also been identified that other crystallo-chemical factors can influence the presence of gallium in the crystal lattices of gibbsite, boehmite or goethite. This interaction has led to potential theories about the origin of bauxites in Jamaica.

The bauxite/alumina industry represents the greatest source of gallium in the world. This discovery is influenced by the fact that gallium concentrates in the sodium aluminate process liquor during the extraction of alumina. During Bayer process operations, the gallium concentration builds up to a steady state concentration that can be detected by analytical methods such as wet chemistry methods or via the utilization of Inductively Coupled Plasma Optical Emission Spectroscopy (ICP-OES) [2].

A 1983 survey of gallium steady state concentrations in four (4) Jamaican alumina refineries revealed that there is a variation in gallium concentrations across operations [3]. Table 1 highlights these details below:

Table 1. 1983 Jamaican Bayer process gallium survey [2].

Plant	Concentration in liquor (ppm Ga)
Plant A	53
Plant B	48
Plant C	85
Plant D	185

The survey indicates that as gallium accumulates in the Bayer process liquor, it is possible to extract it using existing industrial scale gallium extraction methods. The two predominant impactors to the concentration of gallium in liquor include (i) bauxite mineralogy (ii) Bayer process plant design and operating conditions.

Temperature is a key parameter in maximizing the extraction of gallium. It is notable that Plant D, a high temperature alumina refinery, has more than two times the gallium content in its process liquor as its low temperature counterparts. Plant D also had the additional advantage of a higher caustic concentration due to higher evaporation rates.

These findings, identified in the 1980-1990 decade in alumina refining in Jamaica, show that there are good prospects for the Jamaican Bayer process operations to be expanded to extract gallium. Ongoing efforts in the research and development programs at the Jamaica Bauxite Institute aim to:

- (i) Investigate the feasibility in 2023 and beyond, of extracting gallium as a by-product of Jamaican Bayer process operations.
- (ii) Evaluate existing methods for gallium extraction (solvent extraction and ion-exchange resin) and establish the most economic method for extracting gallium from Jamaican Bayer Process liquors.
- (iii) Conduct bench scale, pilot scale and full-scale commissioning of gallium extraction operations as an appendage to Jamaican Bayer process operations.

2. Experiments and Results

Preliminary studies on gallium in Bayer process operations only highlighted the presence of gallium in one sample of sodium aluminate liquor. They did not indicate the dispersion of the gallium through the entire Bayer circuit. In order to get a more thorough understanding of the dispersion of gallium through the Bayer process, a gallium profile was created. Samples collected from plant B in 2022 are highlighted below.

The samples were submitted to the Jamaica Bauxite Institute Laboratory, where the samples were filtered, diluted, and analyzed using the Agilent 5800 ICP-OES.

4. Summary

Gallium concentrations in Jamaican Bauxites were found to be in the range of 48–75 µg/g. This level is found to be comparable to other bauxite rich regions of the world such as Australia, Suriname, Greece and the USA.

Gallium in Jamaican bauxites was found to disperse in the Bayer process during alumina extraction, and predominantly remains in the sodium aluminate liquor. The concentration of the gallium in the liquor continues to increase until a steady state equilibrium concentration is achieved. This equilibrium concentration is dependent on temperature and liquor concentration.

As the global demand for gallium increases, and the relatively high concentration of gallium is detected in Jamaican bauxites, there is room for growth in Jamaican alumina refinery operations to expand to include gallium production as part of its alumina refining activities.

The next phase of this study will aim to operationalize the information that has been collated over the past four decades, via bench scale, then pilot scale extractions of gallium.

5. References

1. Doris Andrea Blackwood, *Gallium and its associations in the Jamaican bauxite/alumina industry*, Doctoral Thesis, University of the West Indies, 1987.
2. Doris Andrea Blackwood et al, Gallium levels of Jamaican bauxites, *Journal of the Geological Society of Jamaica*, June 1982, Volume (5), 77-82.
3. Janice Smith, Gallium extraction from Jamaican bayer liquors: Patent evaluations and status report, *Jamaica Bauxite Institute*, October 1987.
4. Todd Fayram et al, The development and implementation of industrial hydrometallurgical gallium and germanium recovery, *Journal of the Southern African Institute of Mining and Metallurgy*, May 2008, Volume 108, 261-271.